

Weld qualification test report

Report number	LP26-1318-02 WPWQ
Customer	AERISON PTY LTD
Address	51 Miguel Road Bibra Lake WA Australia 6163
Requested by	Paul Thariyan
Purchase Order	WOR-PR-0088
Test activity dates	22/05/2026
Description	Welder qualification testing
Identification	LP26-1318
WPQR No.	WPQR 614
Welders name	Chee Meng Chong (Calvin)
Welders ID	703
Material shape	Plate to plate
Joint type	Fillet - Tee Fillet
Thickness	T1: 6 mm T2: 6 mm
Weld process	MMAW (Position 3F)
Material Grade	ASTM A240 Grade 3CR12
Test results	Refer to the following summary and details on the following pages.



REVOKED

Macro test	Complied
------------	----------



Accreditation No. 15840

Accredited for compliance with
ISO/IEC 17025-Testing

Refer to the following pages for details of test conducted and Signatories.

Issue date : 22/05/2026

Report no. LP26-1318-02 WPWQ, AERISON PTY LTD, Page 1 of 4, Format no. OMS MF-RP-26 WPWQ OMS(Rev. 5.0 20250412)

Macro test

Accredited laboratory	LMATS Perth Laboratory
Job address	LMATS Perth Laboratory
Test specification	AS/NZS 1554.6:2012 - Category 1B, EN ISO 9606-1:2017
Test method	AS/NZS 2205.5.1:2024 (ISO 17639:2022)-Macro test - weld, ISO 17639:2022-Macro test - weld
Specimen location	Location as per specification Standard
Preparation	Cold cutting followed by stage grinding to P#1200 coated abrasives
Etchant & process	10% Oxalic acid electrolytic etching
Weld geometry	Scale indicates 1mm graduation Refer to the photographs on following pages.
Approved tester	Aaron Jamieson

Specimen 1 :

Test date	22/05/2026
Magnification	x 5 approximately (refer to the photograph)
Leg length	7.1 mm, 5.6 mm
Discontinuities	Nil
Comments	The etched cross-section showed complete penetration and fusion with no evidence of cracks, gross porosity or inclusions.
Test results	The test results comply with the specification requirements.

Specimen 2 :

Test date	22/05/2026
Magnification	x 5 approximately (refer to the photograph)
Leg length	6.4 mm, 5.35 mm
Throat thickness	4.2 mm
Discontinuities	Nil
Comments	The etched cross-section showed complete penetration and fusion with no evidence of cracks, gross porosity or inclusions.
Test results	The test results comply with the specification requirements.



Image 1 of 2 - Macro Specimen 1 (1 Graduation = 1mm) M1




Image 2 of 2 - Macro Specimen 2 (1 Graduation = 1mm) M2

Normative general notes

1. Test and inspection items may be discarded after 6 weeks, unless alternative arrangements are made with LMATS.
2. Samples, identification of samples and all job specific details were supplied by the client. The test results relate only to the items tested or sampled.
3. Any stated nominal pipe sizes and nominal thickness of the material were provided by the client.
4. Where applicable, the Measurement Uncertainty (MU) applies to the test results as per LMATS procedure. MU can be obtained by contacting one of LMATS ISO 17025 accredited laboratories.
5. Acceptance criteria is applied from the test specification. If the test specification does not include acceptance criteria, then the test or inspection results should be referred to a competent authority for further action.
6. Refer to the attached revision notes if this report has been revised. This report shall not be reproduced except in full without approval of the issuing laboratory to ensure that parts of a report are not taken out of context. The client or their representatives shall not edit this report.
7. LMATS or its professional indemnity insurance provider do not indemnify the contents within this report or the conformity of a tested product unless the invoice for the reported work is paid in full within the agreed credit terms. Reports will be revoked if the invoice for the completed work is not paid in full.

REVOKED

Abbreviations used in this report

A - No discontinuities detected	KC - Crater crack	RP - Report findings
BT - Burn (melt) Through	KL - Longitudinal crack	SED - Excessive Dressing (underflushing)
C - Comply	KT - Transverse crack	SGI - Incompletely filled Groove
CP - Crater Pipe	LI - lack of Inter-run fusion	SGS - Shrinkage Groove
DNC - Does Not Comply	LP - Incomplete root Penetration	SMG - Grinding Mark
EC - Elongated Cavity (hollow bead)	LR - lack of Root fusion (missed edge)	SMH - Hammer Mark
F - Failed	LS - lack of Side fusion	SMT - Tool Mark (chipping mark)
GP - Gas Pore	NRRD - No Recordable Reflections Detected	SRC - Root Concavity (Suck back)
HiLo - Linear misalignment	NUSID - No unacceptable Surface Indications Detected	SSP - Spatter
IC - Copper Inclusion	P - Passed	SUC(e) - Undercut External
IL - Linear Inclusion (slag line)	p.d. - Processing / film Defects	SUC(i) - Undercut Internal
IN - Inclusion	PG - Localized Porosity	SXP - Excessive Penetration
IO - Oxide Inclusion (wagon tracks)	PL - Linear Porosity	WH - Worm Hole
IT - Tungsten Inclusion	PU - Uniform Porosity	